

Product Data Sheet



Page 1 of 2

DESCRIPTION: 95W-D011 ROADZILLA® WHITE METHYL-METHACRYLATE (MMA) 4:1 EXTRUDE TWO-COMPONENT TRAFFIC

MARKING PAINT

COLOR: WHITE – PART A CATALYST – PART B

CORRESPONDING CODE: 25W-G011 95W-D011

APPLICABLE SPECIFICATION: STATE OF ALASKA - TYPE III AND WSDOT TYPE 4

TYPICAL USE: CROSSWALKS, STOP BARS, SIGNAGE, AND OTHER AREAS WHERE

DURABILITY IS CRITICAL

DRY TIME: LESS THAN 30 MINUTES AT 77°F

COVERAGE: APPROXIMATELY 17 SO. FT. PER GALLON AT 90 MILS

APPROXIMATELY 99 GAL/MILE AT 90 MILS

GLASS BEADS: AT LEAST 12 POUNDS PER 100 SQUARE FEET WITH SWARCO MEGALUX 30/50 GLASS BEADS WITH THE T-13

COATING.

TECHNICAL DATA AND PRODUCT SPECIFICATIONS MAY BE FOUND ON THE REVERSE SIDE OF THIS DOCUMENT.

To avoid slips and falls, do not use Aexcel traffic marking paint on large pedestrian surfaces or inclined surfaces including, but not limited to, ramps, walkways, stairs, crosswalks, and loading zones. As another example, do not paint an entire traffic stall. When the paint is applied to areas where there may be pedestrian traffic, always apply in conjunction with sufficient anti-slip additives to ensure traction. Failure to add anti-slip additives could contribute to falls that could result in serious injury or death.

See ANSI/NFSI B101.1 & ANSI/NFSI B101.3 for guidance on increasing slip resistance

GENERAL INFORMATION

The following information has been provided as a general guideline for the use and disposal of Aexcel traffic marking paints. It is also very beneficial to run a small test in a non-critical area in order to ensure the surface preparation; weather conditions, equipment and product are suitable and working properly.

SURFACE PREPARATION

Care should be taken to ensure that the surface is clean, dry and free of loose material. A simple leaf blower is typically sufficient to remove gravel and dust in most instances. Methacrylates should be applied to unpainted substrates or to previous methacrylate coatings. They will not adhere to existing waterborne or thermoplastic markings. They will adhere to solvent markings, however to ensure bonding, there should be less than 25% of the old coating remaining prior to applications. Other surface conditions, such as areas with large amounts of engine oil buildup or existing epoxy coatings, may require a power-washing procedure or abrading the surface before application of the paint. New concrete and asphalt should be aged for a minimum of 30 days prior to painting. Use caution when striping over a freshly sealed surface. Sealers can affect the adhesion and cure of traffic marking paints. For more information on the surface, please consult with the supplier or applicator of the surface.

WEATHER CONDITIONS AND APPLICATION

Air temperature, surface temperature, humidity and the weather conditions following application are extremely important factors in the success of the products. Do not apply to wet surfaces or over existing painted areas. Aexcel formulates these coatings to be applied without further reduction. They can also be used in conjunction with the application of glass beads to improve reflectivity without sacrificing other properties. Protect fresh lines from traffic until thoroughly dry. **This coating should not be applied to surfaces less that 40^{\circ}F or to surfaces above 110^{\circ}F.**

EOUIPMENT

The equipment must be matched to the paint being applied in order to achieve the proper film thickness and coverage. Methyl-Methacrylate coatings require specialized application equipment and should never be applied using standard equipment. Equipment recommendations are available upon request.

PAINT SELECTION AND SAFETY

Use only paint recommended or specified for each application. Methyl-Methacrylates give off large amounts of heat upon reaction. Mixing volumes of more than five gallons at a time is not recommended due to the exothermic reaction. Shelter the containers when possible and avoid prolonged outside storage. Agitation of the paints by stirring or shaking should be performed in order to ensure uniform consistency, application and performance. Always be sure the containers are sealed tightly during transporting or storing in order to avoid spillage, risk of fire and solvent evaporation. Keep paints away from heat and flame. Consult the MSDS and/or labels for further safety, first aid, and spill or leak procedures.

WASTE DISPOSAL

Comply with all regulations regarding handling, storage and disposal of all hazardous materials and waste. Consult local agencies or disposal companies for individual instructions and requirements. **Improper disposal of paint and their related materials is illegal and may result in large fines.** Please comply with all regulations and minimize waste whenever possible.

NAME: ROADZILLA TM WHITE METHYL-METHACRYLATE (MMA) 4:1 TWO-COMPONENT

TRAFFIC PAINT

COLOR: WHITE – PART A CATALYST – PART B

CODE: 25W-G011 95W-D011

VISCOSITY @ 77°F, Daniel Flow Gauge 12-14 12-14

WEIGHT PER GALLON @ 77°F, Lb.: 15.6 +/- 0.2 16.7 +/- 0.2

TOTAL SOLIDS, % By Weight: 99.0 Min. 98.0 Min.

PROPERTIES AFTER COMBINATION AT 4:1 PART A:PART B BY VOLUME

GEL TIME, Minutes @ 77°F: 15 Maximum

CURE TIME, Minutes @ 77°F: 30 Maximum

HARDNESS, Shore Durameter, Type A-1: 80 Minimum

DRY FILM REFLECTANCE, % of Magnesium Oxide: 85 Minimum

CHEMICAL RESISTANCE: NO EFFECT AFTER SEVEN DAYS IMMERSION IN ANTIFREEZE, MOTOR OIL, DIESEL

FUEL, GASOLINE, CALCIUM CHLORIDE OR TRANSMISSION FLUID

CLEANUP SOLVENTS, Green: CITRO-D Thermoplastic Equipment Cleaner - MGI Traffic Control Products

(Natural - Biodegradable- Organic)

CLEANUP SOLVENT, Conventional: Acetone
REVISION DATE: 4/29/22

CAUTION: The catalyst portion cannot be frozen or stored in freezing temperatures.

*NOTE: For best results, topcoat with at least 12 pounds per 100 square feet with Swarco's Megalux 30/50 glass beads with the T-13 coating. Product data sheets of the beads are available upon request. Different gradations and coverage rates may be required based on the specifics of the installations.

Use of other coatings on the glass beads could affect the cure and durability of the material.



Aexcel Corporation • 7373 Production Drive • Mentor, Ohio 44060 • Phone: 440-974-3800 • Fax: 440-974-3808

The Product data offered herein are, to the best of our knowledge, true and accurate, but all recommendations are made without warranty, express or implied. Since the conditions of use are beyond our control, neither Aexcel Corporation, nor its agents shall be liable for any injury, loss or damage, direct or consequential, arising from the use or the inability to use the product described herein. No person is authorized to make any statement or recommendation not contained in the Product Data, and any such statement or recommendation, if made, shall not bind the Corporation. Further, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents, and no license under the claims of any patent is either implied or granted.